

PLASTIC MOULD STEELS

HARDENABLE CORROSION RESISTANT STEEL

Segmenty aplikácií

Spracovanie plastov

Dostupné výrobné profily

Týčové polotovary*

Plechý

* Uvedené údaje sa týkajú výlučne dlhých výrobkov. Dodržiavajte podrobné vysvetlenia na konci údajového listu (pdf).

Popis produktu

BÖHLER M390 MICROCLEAR - Oceľ na formy na plasty odolná proti korózii vyrobená práškovou metalúgiou s najvyššou odolnosťou proti opotrebovaniu na nástroje, u ktorých sa požaduje najdlhšia životnosť.

Spôsob výroby

Prášková metalurgia

Vlastnosti

- > Húževnatosť a odolnosť proti plastickej deformácii : dobré
- > Odolnosť proti opotrebovaniu : veľmi vysoká
- > Obrobiteľnosť : dobré
- > Rozmerová stabilita : veľmi vysoká
- > Leštiteľnosť : veľmi vysoká
- > Odolnosť proti korózii : dobré
- > Mikročistota : veľmi vysoká

Aplikácia

- > Komponenty pre potravinársky priemysel
- > Priemyselné nože
- > Zdravotníctvo a medicínska technika
- > Matrice na výrobu tabliet
- > Vstrekovanie plastov
- > Lovecké nože
- > Obalový priemysel
- > Vstrekovanie vystužených plastov
- > Závitovky
- > Elektronický priemysel
- > Extrúzia plastov

Chemické zloženie

C	Si	Mn	Cr	Mo	V	W
1,9	0,7	0,3	20	1	4	0,6

Stav pri dodaní**Mäkké žihanie**

Tvrdosť (HB)	max. 280
--------------	----------

Tepelné spracovanie**Žihanie na odstránenie prnutí**

Teplota	max. 650 °C	Soft annealed material: For stress relief annealing after mechanical processing, hold the material at temperature in a neutral atmosphere for 1-2 hours after complete heating, then slowly cool the furnace at 20°C [68 °F]/hour to 200°C [392 °F], then cool in air.
Teplota		Hardened and tempered material: The temperature for stress relief annealing should be approx. 50°C [122 °F] below the previously selected tempering temperature. Other procedure as for stress relief annealing of soft annealed material.

Kalenie a popúšťanie

Teplota	1 100 až 1 150 °C	For hardening, hold the material at the specified temperature for 20-30 minutes after complete heating and quench quickly. Cool the material to approx. 30°C [86 °F]. Immediately afterwards, the material can be deep-frozen for 2 hours (at -80°C [-112 °F]) for residual austenite transformation. Tempering should also be carried out immediately.
Teplota	1 151 až 1 180 °C	For hardening, hold the material at the specified temperature for 5-10 minutes after complete heating and quench quickly. Cool the material to approx. 30°C [86 °F]. Immediately afterwards, the material can be deep-frozen for 2 hours (at -80°C [-112 °F]) for residual austenite transformation. Tempering should also be carried out immediately.
Teplota	200 až 300 °C	Tempering treatment: For maximum corrosion resistance, heat the material slowly and temper once for 1 hour/20 mm material thickness, but for at least 2 hours. Take slow heating into account and cool the material to approx. 30°C [86 °F] after each heat treatment step. Achievable hardness - see tempering diagram.
Teplota	540 až 560 °C	Tempering treatment: For maximum wear resistance (without sub-zero cooling), temper the material 3 times for 1 hour/20 mm material thickness, but at least 2 hours. Allow for slow heating and cool the material to approx. 30°C [86 °F] after each heat treatment step. Achievable hardness - see tempering diagram.
Teplota	510 až 530 °C	Tempering treatment: For maximum wear resistance (with sub-zero cooling), temper the material 3 times for 1 hour / 20 mm material thickness, but at least 2 hours. Allow for slow heating and cool the material to approx. 30°C [86 °F] after each heat treatment step. Achievable hardness - see tempering diagram.

Fyzikálne vlastnosti

Teplota (°C)	20
Hustota (kg/dm ³)	7,54
Tepelná vodivosť (W/(m.K))	16,5
Merná tepelná kapacita (kJ/kg K)	0,48
Merný elektrický odpor (Ohm.mm ² /m)	-
Modul pružnosti (10 ³ N/mm ²)	227

Tepelná rozťažnosť

Teplota (°C)	100	200	300	400	500
Tepelná rozťažnosť (10 ⁻⁶ m/(m.K))	10,4	10,7	11	11,2	11,6

Údaje v tejto brožúre nie sú záväzné a nepovažujú sa za prísluby, slúžia skôr len ako všeobecné informácie. Tieto informácie sú záväzné len vtedy, ak sú výslovne uvedené ako podmienka v zmluve uzavretej s nami. Namerané údaje sú laboratórne hodnoty a môžu sa líšiť od praktických analýz. Pri výrobe našich výrobkov sa nepoužívajú žiadne látky škodlivé pre zdravie alebo ozónovú vrstvu