

NÁSTROJOVÉ OCELE PRE PRÁCU ZA TEPLA

Segmenty aplikácií

Horúce práce

Automobilový priemysel

Dostupné výrobné profily

Tyčové polotovary

Popis produktu

BÖHLER W460 VMR is a double vacuum arc remelted (VAR) material that has been specially adapted for use in the motorsport sector. The steel purity achieved by this special manufacturing technology, combined with the high strength, ensures that a very high fatigue strength can be guaranteed. The high purity also results in very good polishability, which makes the steel a good choice as a tool material for minting coins.

Spôsob výroby

Konvenčná výroba + VAR + VAR

Aplikácia

> Odvetvie motoristického športu

> Razenie

> Diely pre všeobecné strojárstvo

Technické údaje

Označenie materiálu	
BÖHLER patent	Market grade

Chemické zloženie

C	Si	Mn	Cr	Mo	V
0,50	0,20	0,45	4,60	3,00	0,75

Stav pri dodaní

Žiháný

Tvrdosť (HB)

max. 205

Tepelné spracovanie

Žihanie

Teplota	750 až 800 °C	Holding time 6 to 8 hours. Slow, controlled furnace cooling at 10 to 20°C/h (50 to 68 °F/hr) to approx. 600°C (1112°F), further cooling in air.
---------	---------------	---

Žihanie na odstránenie pnutí

Teplota	650 až 700 °C	For stress relief after extensive machining or for complicated tools. Holding time depending on tool size after complete heating 2 - 6 hours in neutral atmosphere. Slow furnace cooling.
---------	---------------	---

Kalenie a popúšťanie

Teplota	1 050 až 1 070 °C	Holding time after temperature equalization: 15 to 30 minutes; Quenching: Oil, salt bath (500 - 550°C [932-1022°F]), air, vacuum; After hardening, tempering to the desired working hardness (see tempering chart).
---------	-------------------	---

Tepelná rozťažnosť

Teplota (°C)	100	200	300	400	500	600	700
Tepelná rozťažnosť (10 ⁻⁶ m/(m.K))	11,1	11,5	11,9	12,3	12,8	13,2	13,6

Údaje v tejto brožúre nie sú záväzné a nepovažujú sa za prísluby, slúžia skôr len ako všeobecné informácie. Tieto informácie sú záväzné len vtedy, ak sú výslovne uvedené ako podmienka v zmluve uzavretej s nami. Namerané údaje sú laboratórne hodnoty a môžu sa líšiť od praktických analýz. Pri výrobe našich výrobkov sa nepoužívajú žiadne látky škodlivé pre zdravie alebo ozónovú vrstvu.